

ATR 35 CH SR HPR

Technical data according to EN 410 and EN 673

4 mm single

4 / 16 / 4 mm double

Corrected emissivity of uncoated glass surface

0.837

Solar Energy Transmission, τ_e	41 %	33 %
Solar Energy Reflection, ρ_e	8 %	13 %
Solar Energy Absorption, a_e	51 %	53 %

Visible Light Transmission, τ_V	39 %	35 %
Visible Light Reflection (External) , ρ_{Ve}	7 %	14 %
Visible Light Reflection (Internal) , ρ_{Vi}	9 %	10 %

Ultraviolet Transmission, τ_{UV}	< 1 %
Ultraviolet Rejection	> 99 %

g value	0.52	0.61
Shading Coefficient	0.60	0.70
Total Solar Energy Rejected	48 %	39 %
Glare Reduction	55 %	60 %

U value, single glazing (W/m ² .K)	5.6	-
U value, double glazing, Air filled (W/m ² .K)	-	2.7

Emissivity, ϵ_n	0.84
--------------------------	------

Thickness without liner	44 μ
-------------------------	----------

Film Colour / Appearance	Medium charcoal
Installation position	Interior
Warranty	5 years**

Installation Notes: Use Film On for installation.

* Please check the complete Film to Glass Thermal Stress Compatibility Guidelines **before** film installation. ** Contact Solutia Performance Films for full details. All values for engineering parameters are determined by the manufacturer and independent testing laboratories.

ATR 35 CH SR HPR

Features & Benefits

- Solar control and daylight privacy film
- Improvement of working conditions due to a reduction in solar heat gain
- Reduction in air-conditioning costs and hence a reduction in energy costs
- Good glare reduction with low visible light reflection
- Excellent anti-UV protection integral to the polyester: helps to reduce fading of textiles, furniture, and works of art
- Scratch resistant coating: Excellent resistance to scratching and abrasion, increasing longevity and allowing easy cleaning
- Interior installation

ATR 35 CH SR HPR Spectra

